

**RECOVER**

Agrotextiles - PP Woven groundcovers

**Functions**

Stimulates the growth of the plants

Prevents the growth of weeds

Not harmful to the environment and prevents the use of herbicides

**Product Specifications**

PROPERTIES	TEST METHOD	VALUE		UNIT	TOLERANCE
		WARP	WEFT		
MATERIAL		PP	PP		
RECYCLED CONTENT	QA-CER system 2	30% post-industrial waste			
RECYCLABILITY		100%			
TISSUE COLOUR		black	black/white		
PATTERN		square 25 cm			
COLOUR LINING		white	black		
TISSUE WEIGHT	ISO 3801	115		g/m <sup>2</sup>	± 5 %
WIDTH		330 - 415 - 515		cm	± 2 cm
LENGTH		100		m	± 2 %

**Environmental Impact Categories**

PROPERTIES	TEST METHOD	VALUE	UNIT	TOLERANCE
GLOBAL WARMING POTENTIAL (Cradle-to-Gate)	EN 15804 +A2	0,16	kg CO2 eq./m <sup>2</sup>	

Compared to the standard PP groundcover, you reach a reduction in CO2 of 35%.

**Technical characteristics**

PROPERTIES		TEST METHOD	VALUE		UNIT	TOLERANCE
			WARP	WEFT		
BREAK ELONGATION		ISO 13934-1	20	17	%	± 20 %
TENSILE STRENGTH		ISO 13934-1	1100	850	N/5cm	± 20 %
PERFORATION RESISTANCE		EN ISO 13433	15		mm	MAX
UV-STABILIZATION		ISO 4892-3 cycle 3	≅ 900		kLy	
SHRINKAGE		15' à 70°C	1,0	1,0	%	MAX
WATERPERMEABILITY		ISO 11058	0,010		m/s	± 50 %
LIGHT TRANSMISSION		NF G 07-162	<1		%	
REMARKS		UV-Stabilization : Based on QUV testing min 3700 h (cycles of 5 h light exposure UV-A 340 nm 0,83 W/m² at 50°C and 1 h water spray), which corresponds theoretically to a solar irradiation of 900 kLy. In a climate zone of 90 kLy/y (Western Europe) this corresponds to 10 years.				

This information contained in this document is based on testing carried out by our laboratory or external research institutes and literature data, and based on Mean Values. This TDS is valid until further notice. To the best of our knowledge and at the time of publication, this information is true and accurate. It shall however, in no event be held to constitute or imply warranty undertaking express or implied commitment from the part of BTT. No liability whatever can be accepted by BTT with regard to the handling, processing or use of the product concerned which must in all cases be used in accordance with all applicable laws and regulations. The mentioned characteristics are not valid when the fabric has been in contact with sulphur-, chlorine-, iron- and bromine derivatives, as well as with copper sulphates and if the product is not installed and used in strict accordance with the installation instructions.