

TECHNICAL DATASHEET

Terralys LF 17/17

Terralys LF 17/17 is a polypropylene woven slit film geotextile, manufactured into a dimensionally stable network, ensuring that filaments retain their relative positions.

Terralys LF 17/17 is inert to biological degradation, and resists most chemicals, alkali and acids encountered in natural soils.

Mechanical properties	Test method	MARV ENGLISH	MARV METRIC
Grab Tensile Strength (MD x CMD)	ASTM D4632	124 lbs x 101 lbs	550 N x 450 N
Grab Elongation (MD x CMD)	ASTM D4632	25 % x 25 %	25 % x 25 %
Trapezoid Tear Strength (MD x CMD)	ASTM D4533	60 lbs x 60 lbs	60 N x 60 N
CBR Puncture	ASTM D6241	450 lbs	2000 N
Permittivity	ASTM D4491	0.10 sec ⁻¹	0.10 sec ⁻¹
Water Flow Rate	ASTM D4491	8 gal/min/ft ²	300 L/min/m ²
Apparent Opening Size*	ASTM D4751	30 US Std. Sieve	0.60 mm
UV Resistance (500 hrs)	ASTM D4355	80 %	80 %

**Maximum roll average value*

Descriptive characteristics	Test method	TYPICAL ENGLISH	TYPICAL METRIC
Mass per unit area	ASTM D5261	2.7 oz/y ²	92 g/m ²

Note: The values presented in the tables above are indicative, they are offered solely to provide possible suggestions. We reserve the right to alter the results of these materials without prior notice. As the installation and the conditions of use are beyond our control, BTT cannot accept responsibility for the performance of any of these products. The properties listed herein are provided as information only and in no way can create any warranty.